

S.N.S.157//1980 ١٩٨٠/١٥٧ المواصفة القياسية السورية رقم
ASPHALT

CHARACTERISTICS	REQUIREMENTS		TEST METHODS
	GRADE60/70	GRADE80/100	
Penetration at 25 Ć Min.	60-70	80-100	IP – 49/76
Softening point (R.B)Ć	46-55	40-50	ASTM D –87/74
Ductility cm.at25Ć Min.	100	100	IP – 32/55/75
Flash point (open cup)Ć Min.	250	220	ASTM D –92/73
Solubility in CS2 % Wt. Min.	99	99	ASTM D –2042/66/72
Loss on heating at 163Ć for4hrs. % Wt. Max.	1.0	1.0	IP – 45/58/74
Percent of decrease in penetration after heating at 163Ć for 4hrs .% Wt. Max	25	30	IP – 49/76

إعداد
مدير الجودة والسلامة المهنية والبيئة
المهندس سمير الخالد